


व्यावसायिक परीक्षण रिपोर्ट
COMMERCIAL TEST REPORT

संख्या/ No.: ROTAVATOR-285/2524/2020
माह/Month : September, 2020

THIS TEST REPORT VALID UP TO : 30th SEPTEMBER, 2027



**SONALIKA, SLCHAMSR-10 ROTAVATOR
(TRACTOR MOUNTED)**



भारत सरकार

Government of India

कृषि एवं किसान कल्याण मंत्रालय

Ministry of Agriculture and Farmers Welfare

कृषि, सहकारिता एवं किसान कल्याण विभाग

Department of Agriculture, Cooperation and Farmers Welfare

उत्तरी क्षेत्र कृषि मशीनरी प्रशिक्षण एवं परीक्षण संस्थान

Northern Region Farm Machinery Training and Testing Institute

ट्रैक्टर नगर, सिरसा रोड, हिसार, (हरियाणा) - 125 001

Tractor Nagar, Sirsa Road, HISAR (Haryana)-125 001

[ISO 9001:2015 CERTIFIED]

Website: <http://nrfmtti.gov.in/>

E-mail: fmti-nr@nic.in

Tele./FAX: 01662-276984

4.11 Lubricants:

Sl. No.	Particulars	As recommended by the manufacturer	As used during test
1	Primary Gear box	EP-140	Oil originally filled in the rotavator was not changed
2	Secondary Gear box	EP-140	
3	Rotor Hub	EP-140	
4	Propeller Shaft	Not specified	M.P. Grease

5. RUNNING – IN

Rotavator was run in for 1.27 hour before field performance test.

6. LABORATORY TEST

6.1 Hardness: - The surface hardness of blade was recorded as under: -

Description	As per IS: 6690:1981 (HRC)	Hardness as observed (HRC)	Remarks
Edge portion	53 to 59	52	Does not conform
On shank portion	37 to 45	52	Does not conform

6.2 Chemical composition

The chemical composition of blades is tabulated as under:-

Constituents	As per IS: 6690-1981		Composition as observed (% of weight)	Remarks
	Carbon Steel	Silicon Manganese steel		
Carbon (C)	0.70 -0.85	0.50-0.60	0.3605	Does not conform
Silicon (Si)	0.10 -0.40	1.50-2.00	0.3182	Conforms to carbon steel
Manganese (Mn)	0.50 -1.0	0.50-1.00	1.1935	Does not conform
Sulphur (S)	0.05(max)	0.05(max)	0.0261	Conforms
Phosphorous (P)	0.05(max)	0.05(max)	0.0331	Conforms

7. FIELD PERFORMANCE TEST

The field tests of the rotavator comprising of Wet land and dry land operation were conducted for 10 and 26 hours respectively to assess the performance test is reported in **Annexure-I & III** for wet land and dry land operation respectively.

Observations of field performance test is summarized in the ensuing table:-



Summary of Field Performance Test

Sl. No.	Parameters/operations	Wet land operation (Puddling)	Dry land operation
I	II	III	IV
1.	Tractor used	Sonalika 60Rx	Worldtrac (MST)
2.	Gear used	L-3	L-3
3.	Type of soil	Sandy loam	
4.	Average soil moisture (%)	--	16 to 19
5.	Average depth of standing water (cm)	6.2 to 6.6	--
6.	Bulk density of soil (g/cc)	--	1.67 to 1.83
7.	Average speed of operation (kmph)	2.43 to 2.45	2.39 to 2.52
8.	Avg. travel reduction (%)	-0.60 to 1.95	--
9.	Avg. wheel slip (%)	--	-2.05 to 0.53
10.	Average depth of puddle (cm)	18.9 to 24.5	--
11.	Average depth of cut (cm)	--	12.0 to 13.5
12.	Avg. effective width (cm)	--	281 to 287
13.	Area covered (ha/h)	--	0.557 to 0.615
14.	Time required for one ha (h)	--	1.63 to 1.80
15.	Field efficiency (%)	--	82 to 87
16.	Puddling index (%)	86 to 89	--
17.	Fuel consumption		
		l/h	3.82 to 4.37
		l/ha	9.81 to 11.46
18.	Average PTO power utilized (kW)	--	NR

7.1 Wet Land operation

7.1.1 The tractor was fitted with half cage wheel on rear pneumatic traction wheel for conducting the puddling operation. The brief specification of half cage wheel is given in Annexure-I

7.1.2 Quality of work

- i) The depth of puddle was recorded as 18.9 to 24.5 cm.
- ii) The puddling index was recorded as 86 to 89 %.

7.2 Dry land operation**7.2.1 Rate of work**

- i) The rate of work was recorded as 0.557 to 0.615 ha/h, and the speed of operation varies from 2.39 to 2.52 kmph.
- ii) The time required to cover one hectare was recorded as 1.63 to 1.80 h

7.2.2 Quality of work

- i) The depth of operation was recorded as 12.0 to 13.5 cm.
- ii) Average effective width was observed as 281 to 287 cm.
- iii) Field efficiency was observed as 82 to 87 %.



ROTA VATOR-285/2524/2020	SONALIKA, SLCHAMSR-10 ROTA VATOR (TRACTOR MOUNTED) (COMMERCIAL)
---------------------------------	----------------------------------------------------------------------------

7.3 Labour requirement

In all, two skilled operators are needed to ensure continuous operation of rotavator for day long period.

7.4 Wear analysis (on mass basis)

Wear of hatchet blades (on mass basis) was measured and recorded in ensuing table:

Percentage wear of rotavator blades on mass basis

Sl. No.	Initial mass of blade (g)	Mass of blade after 37 hr. of operation (g)	Difference of weight (g)	Percentage of wear (%) after 37 hr.	Percentage of wear on hour basis (%)
1.	1004.3	988.0	16.3	1.62	0.04
2.	1002.5	987.0	15.5	1.55	0.04
3.	999.8	982.1	17.7	1.77	0.05
4.	1027.1	1011.9	15.2	1.48	0.04
5.	1000.7	987.3	13.4	1.34	0.04
6.	1011.3	999.3	12.0	1.19	0.03
7.	993.9	982.0	11.9	1.20	0.03
8.	994.7	982.8	11.9	1.20	0.03
9.	999.4	984.7	14.7	1.47	0.04
10.	996.6	982.6	14.0	1.40	0.04
11.	998.9	988.0	10.9	1.09	0.03
12.	996.0	983.6	12.4	1.24	0.03

8. EFFECTIVENESS OF SEALINGS

After completion of wet land operation for 10 hours, the rotavator was dismantled for checking the effectiveness of sealing provided against ingress of dust, and water/mud in various sub-assemblies/components. The observations are given in ensuing table:-

Sl. No.	Location	Whether ingress of mud and/or water was observed (Yes/No)
1.	Primary reduction gear box	No
2.	Secondary reduction gear box	No
3.	Rotor assembly (hub)	No

9. EASE OF OPERATION & ADJUSTMENTS

No noticeable difficulty was observed during the operation and adjustment of rotavator.

10. DEFECTS, BREAKDOWN AND REPAIRS

No noticeable defect or breakdown was observed during the test.

11. CRITICAL TECHNICAL SPECIFICATION

Deferred till 31.12.2020 vide Ministry O.M. No 13-13/2020 M&T, (I&P) dated 24.04.2020





ROTAVATOR-285/2524/2020	SONALIKA, SLCHAMSR-10 ROTAVATOR (TRACTOR MOUNTED) (COMMERCIAL)
-------------------------	-------------------------------------------------------------------

12. COMMENTS AND RECOMMENDATIONS

- 12.1** The Dimension of three point linkage of implement does not conform, in toto, to the requirements of IS: 4468(Part-1)-1997 and therefore, it may be looked into for corrective action.
- 12.2** The Dimensions of PIC of implement and PIC yoke bore does not conform, in toto, to the requirements of IS: 4931-1995 and therefore, it may be looked into for corrective action.
- 12.3** The chemical composition of blades does not conform, in toto, to the requirements of IS: 6690-1981. This needs to be looked into for corrective action.
- 12.4** The hardness of blades does not conform, to the requirements of IS: 6690-1981. This needs to be looked into for corrective action.
- 12.5 Technical literature:-**
One booklet entitled "Owner's manual" was provided for reference during test. The same, however, needs to be updated as per IS-8132-1999.

TESTING AUTHORITY

RINKU PRASAD GUPTA TECHNICAL ASSISTANT	
P. K. PANDEY DIRECTOR	

Test Report is compiled by C. Veeranjanyulu. Senior Technician

13. APPLICANT'S COMMENTS

Para No.	Our reference	Applicant comments
13.1	12.1	We will take care the same in our regular production/vendor end.
13.2	12.2	The dimension of PIC of implement will be improve at vender/production end as pre IS: 4931-1995.
13.3	12.3	The chemical composition of blades will be improve at vender/production end as pre IS: 6690-1981.
13.4	12.4	The hardness of blades will be improve at vender/production end as pre IS: 6690-1981.
13.5	12.5	Technical literature will be updated as per IS: 8132-1999.